

## Technical Specifications

|   | Unit             | Nominal Value | Test Method   |
|---|------------------|---------------|---------------|
| Lenght (w)                                | mm               | 1000          | TS EN 544     |
| Width (h)                                 | mm               | 320           | TS EN 544     |
| Tensile Strenght (Lenght-Width)           | N/50 mm          | 600/400       | TS EN 12311-1 |
| Nail Tearing Resistance                   | N                | 100           | TS EN 12310-1 |
| Heat Resistance                           | °C               | ≥ 120         | TS EN 1427    |
| Watertightness - Mass of Bitumen          | g/m <sup>2</sup> | ≥1300         | TS EN 544     |
| Adhesion of Mineral Granules; max.        | g                | 2,5           | TS EN 12039   |
| Blistering Resistance                     | -                | Pass          | TS EN 544     |
| Flow Resistance at High Temperature; max. | 90°C             | 2 mm          | TS EN 1110    |
| Resistance to UV Radiation                | 60 cycles        | Pass          | TS EN 1297    |
| Water Absorption                          | -                | < %2          | TS EN 544     |
| Artificial Aging                          | -                | Pass          | TS EN 1926    |
| Reinforcement                             | g/m <sup>2</sup> | ≥ 80          | TS EN 544     |

## Flammability

|                  | Unit | Test Method   |
|------------------|------|---------------|
| Reaction to Fire | E    | TS EN 13501-1 |

## BUNDLE SPECIFICATIONS

| Quantity     |                | Loading       | Covering Area          |                         |
|--------------|----------------|---------------|------------------------|-------------------------|
| Each /Bundle | Bundle/Palette | Palette/Truck | m <sup>2</sup> /Bundle | m <sup>2</sup> /Palette |
| 18           | 57             | 12            | 2,61                   | 148,77                  |